



# VT-90H

## Laminate/Prepreg

UL Approval: E214381 Version: B7/40 /41

### General Information

- > Tg 250° C
- > High Td
- > Improved Fracture Toughness
- > Low Z-axis CTE
- > Non-Brominated Chemistry



**Validation Services LISTED**

### Application

- > Chip Manufacturers
- > Engine/Flight Controls
- > Power Supply/Backplane
- > Military and Burn-in Board

### Availability

- > Core Thickness: 0.002" (0.05mm) to 0.125"(3mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 6oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 2113, 2313, 3313, 2116, 1080, 106 etc

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23° C (73° F)	Below 5° C (41° F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

#### CORPORATE HEADQUARTERS

**Ventec Electronics Co. Ltd.**  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

**Ventec Europe**  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

**Ventec USA**  
720 Lee St., Elk Grove Village,  
Illinois, IL 60007,  
United States of America  
T: +1 630-4221627  
Email: saleseast@ventec-usa.com

www.ventec laminates.com

# VT-90H

## Laminate/Prepreg

UL Approval: E214381 Version: B7 /40 /41

### IPC-4101E /40 /41

Properties		Test Method	Units	Specification	Typical Value
<b>Thermal Properties</b>					
T <sub>g</sub>	DSC	IPC-TM-650 2.4.25	°C	–	–
	TMA	IPC-TM-650 2.4.24	°C	200 minimum	250
T <sub>d</sub>		ASTM D3850	°C	–	408
T260		IPC-TM-650 2.4.24.1	Minute	–	>60
T288		IPC-TM-650 2.4.24.1	Minute	–	>60
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>1200
Z-axis CTE	Before T <sub>g</sub>	IPC-TM-650 2.4.24	ppm/°C	–	50
	After T <sub>g</sub>	IPC-TM-650 2.4.24	ppm/°C	–	145
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	–	1.2
X/Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~12
MOT		UL 94	°C	–	140
<b>Electrical Properties</b>					
Dielectric Constant @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	–	5.4 maximum	4.05
Dissipation Factor @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	–	0.035 maximum	0.012
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.4.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 [30] minimum	1200~1400 [54]
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 4 (100-175)
Arc Resistance		ASTM D495	Second	120 minimum	150
<b>Mechanical Properties</b>					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	6~9 (1.05~1.58)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	5.14 (0.90) minimum	6~9 (1.05~1.58)
Flexural Strength	Warp	IPC-TM-650 2.4.4	KPsi (MPa)	60 [415] minimum	87 [600]
	Fill	IPC-TM-650 2.4.4	KPsi (MPa)	47 [325] minimum	72 [500]
<b>Physical Properties</b>					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	1.0 maximum	0.28
Flammability		UL-94	Rating	HB minimum	HB

Note: All test data provided are typical values and are not intended to be specification values.

Disclaimer: The information and data contained in this technical literature is based on data and knowledge correct at the time of publishing/printing and is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

#### CORPORATE HEADQUARTERS

##### Ventec Electronics Co. Ltd.

308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

##### Ventec Europe

Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

##### Ventec USA

720 Lee St., Elk Grove Village,  
Illinois, IL 60007,  
United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

www.ventec laminates.com